

NFRC 101-2017



NFRC Errata and Addendum Log

E1A1 (April 2017)

Table C.1: Thermophysical Properties of Solid Materials

Participant	Product	Density kg/m ³	Conductivity			Emissivity	Expiration Date
			W/m•K	Btu/hr•ft•F	Btu•in/hr•ft ² •°F		
SaftiFirst	Fire Resistant Inner Layer	1160	0.307	0.178	2.13	0.9	7/1/2021

E1A0 (February 2017)

Table C.1: Thermophysical Properties of Solid Materials

Participant	Product	Density kg/m ³	Conductivity			Emissivity	Expiration Date
			W/m•K	Btu/hr•ft•F	Btu•in/hr•ft ² •°F		
Andersen Corporation	CPA Fiberglass Material	1675	0.159	0.092	1.105		12/31/20192020
Zola Windows	V2-V1 Foam Insulation	538	0.071	0.041	0.489	-	12/31/2020
Zola Windows	V1-V2 Foam Insulation	205	0.039	0.023	0.270	-	12/31/2020

E0A0 (January 2017)

Table C.1: Thermophysical Properties of Solid Materials

Participant	Product	Density	Conductivity			Emissivity	Expiration Date
		kg/m ³	W/m•K	Btu/hr•ft•F	Btu•in/hr•ft ² •°F		
3M™	VHB™ Structural Glazing Tapes- 4972	720	0.143	0.083	0.992	-	<u>5/11/2016</u> <u>7/1/2020</u>
3M™	VHB™ Structural Glazing Tapes- B23F	720	0.138	0.08	0.957	-	<u>5/11/2016</u> <u>7/1/2020</u>
3M™	VHB™ Structural Glazing Tapes- G23F	720	0.137	0.079	0.95	-	<u>5/11/2016</u> <u>7/1/2020</u>
Royal/Kömmerling	Kodispace 4SG	1191.74	0.241	0.139	1.67	-	<u>6/11/2016</u> <u>7/1/2020</u>
Andersen Corporation	CPA Fiberglass Material	1675	0.159	0.092	1.105		<u>1/8/2017</u> <u>12/31/2019</u>

In addition to these changes, ballots approved by NFRC membership at the Fall 2016 Membership Meeting in Denver, Colorado, were incorporated into the 2017 document. These ballots may be reviewed via this page: <https://nfrccommunity.site-ym.com/page/BallotListF16>.